



F2255

Sunprene Tubing (PVC)



Product Description

Grayline F2255 is a flexible polyvinyl chloride tubing that is manufactured using Sunprene PVC resin. It is primarily used in automotive applications, electric motors, and a wide range of other wire harnessing applications.

*Standard Packaging: Reels or Cut to Customer Specifications.
Standard Color: Natural, Black
Custom Sizes & Colors Available Upon Request*

Specifications

- EU Directive 2000/53/EC (ELV)
- EU Directive 2011/65/EU (RoHS2)
- FMVSS302

Features

- Operating Temperature is -40°C to 105°C
- Low Temperature Flexibility
- Lead-Free

PROPERTY	TYPICAL VALUE	TEST METHOD
Durometer Hardness, Shore A (15 Seconds)	75	ASTM D2240
Tensile Strength (psi)	2,500	ASTM D412
Elongation (%)	300	ASTM D412
Specific Gravity	1.27	ASTM D792
Brittleness Temperature, Pass $^{\circ}\text{C}$	-40	ASTM D746

The values listed in this bulletin, to the best of our knowledge, are accurate. They are typical performance results and are not intended to be used as design data. We disclaim all liability in connection with the use of information contained herein or otherwise.