



FL75-VTN

Viton® Fluoroelastomer Tubing



Product Description

Grayline FL75-VTN tubing offers excellent resistance to oils, fuels, lubricants, and most mineral acids. It resists aliphatic and aromatic hydrocarbons (carbon tetrachloride, benzene, toluene, & xylene), which would cause conventional rubbers to disintegrate.

Viton® tubing also stands up well to compression set, outdoor exposure (ozone, UV, weathering), mold & fungus, and compression set (even at high temperatures).

Standard Packaging: Coils
Standard Color: Black

Specifications

- EU Directive 2011/65/EU (RoHS2)

Features

- Operating Temperature is -34°C to 204°C
- UV, Ozone & Chemical Resistant
- Made from 100% pure Viton® Synthetic Rubber

Standard Sizes

ID (Inches)	OD (Inches)	Wall (Inches)	Standard Coil Length (FT)	Weight (LB/100 FT)
1/32	3/32	1/32	50, 100	.50
1/32	5/32	1/16	50	1.48
1/16	1/8	1/32	50, 100	.74
1/16	3/16	1/16	50, 100	1.99
1/8	1/4	1/16	50, 100	2.97
3/16	5/16	1/16	50, 100	3.96
1/4	3/8	1/16	25, 50	4.94
1/4	1/2	1/8	50	11.86
5/16	7/16	1/16	25, 50	5.94
3/8	1/2	1/16	25, 50	6.92
3/8	9/16	3/32	25, 50	11.16
3/8	5/8	1/8	25	15.82
1/2	3/4	1/8	25	19.77
3/4	1	1/8	25	27.68
7/8	1	1/16	25	14.83

Property	Typical Value
Durometer Hardness, Shore A	75
Tensile Strength (psi)	1,600
Elongation (%)	150
Brittleness Temperature, Pass °C	-34

ID/OD Measurement Tolerances	
0.000" - 0.100"	±.010
0.101" - 0.160"	±.013
0.161" - 0.250"	±.016
0.251" - 0.400"	±.020
0.401" - 0.630"	±.025
0.631" - 1.000"	±.032

The values listed in this bulletin, to the best of our knowledge, are accurate. They are typical performance results and are not intended to be used as design data. We disclaim all liability in connection with the use of information contained herein or otherwise. Viton® is a reg. TM DuPont Dow Elastomers